

# **Bond Idro**

# Reinforcing, impregnating, internally reactive waterproofing latex



Adhesive latex composed of an emulsion of binding and reinforcing synthetic polymers, reactive waterproofing agents, for flexibilising and hydrophobising plaster, mortar and grout.

CUSTOMS CODE: 3816 0000 COMPONENTS: Single-component

APPEARANCE: Liquid
AVAILABLE COLORS: White

PACKAGING AND DIMENSIONS: Plastic can 25 kg - Plastic can 5 kg - Plastic can 10 kg

#### **FEATURES AND BENEFITS**

The action of BOND HYDRO is based on the interaction of a particular reactive agent, hydrophilic in its original form, potentially hydrophobic by reaction with the cement and lime compounds.

# **FIELDS OF APPLICATION**

Waterproof, reinforcing protection of external walls in concrete, cement or lime-based plaster, concrete floorings, etc. Production of protective coating and waterproofing mixtures based on hydraulic binders. Curing protection with impregnating effect, of fresh conglomerates. Packaging of jointing mortars for bedding blocks of fair-faced cement-clay.

#### ALLOWED SUPPORTS

Plasters - Concrete - Cement-based or lime-based mortars

## MODE OF USE

Remix the product before use and then prepare a solution as indicated in the tables below, depending on the intended use.

#### **APPLICATION METHODS**

To be added to other components - Scrubbing brush - Sprayer



## **TOOL CLEANING**

Water

# **KEY FEATURES**



Density: 1.10 kg/dm<sup>3</sup>



Shelf-life: 12 months



Temperature of use: +5 / +35 °C



Nonflammable



Solvent-free

# **TECHNICAL SPECIFICATIONS**

Non-toxic material

# **CONSUMPTION**

Refer to the table shown in the product datasheet.

## STORAGE AND CONSERVATION

Protect from freezing. Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Store the product at a temperature between +5°C and +35°C.

# **PHOTO GALLERY**







#### ADDITIONAL CONTENT



# Indicative dosages

The modalities and the quantities of use vary in function of the need for use, based on the mixtures indicative below:

| USE  | Bond Idro /<br>water ratio | Binder / inert ratio                   | Maximum inert size   |
|--|----------------------------|--|----------------------|
| Mortars for restoration Thickness ≤ 1 cm Thickness> 1 cm | 1:1<br>1:2                 | From 1: 1 to 1: 3<br>From 1: 2 to 1: 4 | 1 - 3 mm<br>2 - 6 mm |
| Plaster  | 1:3                        | From 1: 1 to 1: 3                      | 1 - 3 mm             |
| Grout  | 1:1                        | Binder only 3 - 4 parts by weight      |                      |
| Consolidation of plaster and masonry                     | From 1:1 to 1:2            |  |                      |

#### **WARNINGS AND PRECAUTIONS**

It is always essential to carry out preliminary tests for an accurate definition of the mixtures to use, and to check the suitability of the product on the basis of the specific requirements. The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

