

Rasogrey

Thixotropic, fibre-reinforcing structural cement skim coat



Structural, fibre-reinforced thixotropic cement skim coat, with excellent adhesion characteristics, resists compression, bending and abrasion, etc. Ideal for structural renovation of works and manufactured pieces in deteriorated concrete. Apply using a trowel.

CUSTOMS CODE: 3824 5090

COMPONENTS: Single-component

APPEARANCE: Powder

AVAILABLE COLORS: Gray

PACKAGING AND DIMENSIONS: Bag 25 kg

OBTAINED CERTIFICATIONS AND REGULATIONS



FEATURES AND BENEFITS

Rheoplastic, thixotropic, structural, composite skim coat with a special cement and select silicate aggregates base, fibre-reinforced with a balanced mix of polypropylene fibres READYMESH and calcium meta-silicate micro-fibres, with the addition of specific agents with a high rate of micro-silicates. It provides, after hardening, high performance in terms of intrinsic permeability, resistant to run-off and hydrolysing activity, mechanical resistance, to abrasion and cavitation, anti-carbonising properties, chemical-physical stability, resistant to atmospheric aggression and run-off waters. It has three-dimensional fibre-reinforcement, provides high hold; it is dimensionally stable (compensated shrinkage).

FIELDS OF APPLICATION

Repairs and protective coatings of civil building works in concrete (pillars, walls, balcony cornices, etc.).

ALLOWED SUPPORTS

Plasters - Concrete - Cement-based or lime-based mortars - Prefabricated concrete

PREPARATION OF SUPPORTS

The application surfaces should be clean, free of containment, inconsistent and incoherent parts, dust, etc., conveniently saturated with water to reach the "saturated to dry surface" condition.

MODE OF USE

Place approx. 2/3 of water in the mixer, adding Rasogrey and the remaining water; continue mixing until you obtain an even mix free of lumps. The mixing water should be approx. 18 - 20% of the weight of the bag. Having completed mixing, wait a few minutes before applying. Addition of Bond HG to the mixing water, (approx. 0.5 litres per 25kg bag of product) allows further improvement in terms of adhesion, hold, impermeability, workability, modelling and deformation capacity.

APPLICATION METHODS

Brick trowel - Finishing trowel - Spatula

TOOL CLEANING

Water


KEY FEATURES

↔ Max. recommended thickness: 10 mm


→← Min. recommended thickness: 2 mm


 Nonflammable


 Shelf-life: 12 months


 Use wearing protective gloves

 Maximum diameter of aggregate: 0.6 mm

 Mix with water: 18 %

 Pot-life: 60 min

 Temperature of use: +5 / +35 °C

 UV-resistant

TECHNICAL SPECIFICATIONS

UNI EN 12190
Compressive strength after 1 day > **4 N/mm²**

UNI EN 12190
Compressive strength after 28 days > **21 N/mm²**

UNI EN 13036-4
Skid resistance **73 mm**

pH > **12**

UNI EN 1015-6
Density **1800 g/l**

UNI EN 1015-18
Capillary absorption **0.49 kg•h^{0.5}/m²**

UNI EN 1015-17
Chloride content <**0.01 %**

UNI EN 12190
Compressive strength after 7 days > **15 N/mm²**

UNI EN 196/1
Flexural strength after 28 days > **5 N/mm²**

EN 13501-1
Reaction to fire **A1**

UNI EN 1015-12
Bonding force **1.8 N/mm²**

EN 13142
Static elastic modulus **13000 N/mm²**

UNI EN 13687-1
Determination of thermal compatibility **1.7 MPa**

CONSUMPTION

Approximately 1.8 kg/m² of Rasogrey for each millimetre of thickness to be made.

STORAGE AND CONSERVATION

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



Produced and distributed by **AZICHEM srl**
Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
Tel: +39 0376.604185 / 604365
Fax: +39 0376 604398
www.azichem.com - info@azichem.com

Update of **21-10-2020**
Terms of sale and legal notices available at
<https://www.azichem.com/general-sales-conditions>
Total pages of this document: 3

PHOTO GALLERY



ADDITIONAL CONTENT



WARNINGS AND PRECAUTIONS

Do not apply in the presence of direct sunshine or strong ventilation. Prolonged care for protection and damp seasoning of the surfaces created. The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com. It is forbidden to dispose of the product and/or packaging in the environment.



Produced and distributed by **AZICHEM srl**
Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
Tel: +39 0376.604185 / 604365
Fax: +39 0376 604398
www.azichem.com - info@azichem.com

Update of **21-10-2020**
Terms of sale and legal notices available at
<https://www.azichem.com/general-sales-conditions>
Total pages of this document: 3