


Readymesh MX-500

High performance 50mm steel fibres



Readymesh MX-500 is a special carbon steel fibre, obtained by the extrusion and cutting of high-strength steel wire. Its special double-hooked form gives it a remarkable shear strength, thus conferring the concrete with excellent post-cracking structural strength even at low doses. Readymesh MX-500 significantly increases the mechanical performance of the structure in terms of toughness, ductility, fatigue, dynamic stress, shock, wear, tensile and shear strength and even post-cracking and damage behaviour.

CUSTOMS CODE: 7326 2000 COMPONENTS: Single-component

APPEARANCE: Fibers
AVAILABLE COLORS: Steel

PACKAGING AND DIMENSIONS: Bag 20 kg - Pallet: 50 x (Bag 20 kg)

OBTAINED CERTIFICATIONS AND REGULATIONS



FIELDS OF APPLICATION

General preparation of fibre-reinforced concrete with high pre and post-cracking performance. Ideal for industrial flooring and prefabrications.

MODE OF USE

"Readymesh MX-500 fibres must be added to the concrete during mixing. It is recommended to pour the fibres directly onto the loading belt of the concrete mixer during the loading of the aggregates. Alternatively, it is possible to add them directly into the mixer after loading the concrete. In this case, add the fibres a little at a time so that they are well-distributed in the cement mix and extend the mixing time by at least one minute for every 20 kg of fibres added in order to achieve optimal distribution. Conglomerates with Readymesh MX-500 can be easily transported and used with pumps, joiners, vibratory finishing machines, roadway extruders (e.g. slipform paver), etc."

KEY FEATURES



Density: 7.8 kg/dm³



Double hook geometry



Unlimited shelf-life



UV-resistant



Diameter: 0.75 mm



Lenght: 50 mm



Use wearing protective gloves

TECHNICAL SPECIFICATIONS

Breaking load longitudinal 1100 N/mm²

12 kg/m3

Linear development 3270 m/m³

Non-toxic material

Nominal length 50 mm

Static elastic modulus 210000 N/mm²

Effective length **54.5 mm**

Number of filmanets 5000 nr/kg

Aspect ratio (I / d) 67

CONSUMPTION

Variable according to the type of work to be carried out and/or performance to be achieved.

PHOTO GALLERY







ADDITIONAL CONTENT

×



WARNINGS AND PRECAUTIONS

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

