


Readymesh PF

Monofilament stranded macro-fibre structural for industrial flooring



Readymesh PF is a stranded structural polyolefin macro-fibre, high-performance, specific for the realisation of continuous surfaces made of concrete, it can also be used in replacement of traditional steel reinforcement. The texture, length and surface finishing of Readymesh PF was designed and developed specifically for "exposed" applications, such as industrial floors made of concrete. Readymesh PF are available in two different lengths: Readymesh PF-180 = 18 mm; Readymesh PF-540 = 54 mm

CUSTOMS CODE: 5404 1200 COMPONENTS: Single-component APPEARANCE: Twisted fibers AVAILABLE COLORS: White

PACKAGING AND DIMENSIONS: Hydro degradable bag 1 kg - Small bag 5 kg - Pallet: 42 x (Box 10 Kg) - PF-540 Box: 10 x (Hydro degradable bag 1 kg) - PF-180 Box: 7 x (Hydro degradable

bag 1 kg)

OBTAINED CERTIFICATIONS AND REGULATIONS



FEATURES AND BENEFITS

The addition of Readymesh PF to the mixture gives the concrete and the resulting manufacture a greater resistance to the forces of traction/bending, reduces the risk of breakage and "spalling" of the concrete component in the corners and edges, drastically reduces the phenomenon of cracks due to shrinkage during the first hours of curing of the concrete. The particular shape and consistency, allows Readymesh PF not to interfere with the process of mechanical floating typical of industrial floors made of concrete, thus allowing a good surface finish. In addition, the use of Readymesh PF instead of the traditional armour of steel is a great saving of costs of material and installation times (in addition to being lighter, environmentally friendly and safe than electrowelded mesh).

FIELDS OF APPLICATION

Industrial flooring, also in replacement of steel mesh. Prefabrication. Widespread three-dimensional high anisotropy reinforcement of concretes in general.

ALLOWED SUPPORTS

Concrete



MODE OF USE

Add the fibres to the concrete during mixing. Mix, with the drum of the mixer truck at full speed, for at least one minute for each m³ of concrete. The dosage, depending on the use, is normally included between 1 to 6 kg/m³ In the case of industrial flooring.

APPLICATION METHODS

To be added to other components

KEY FEATURES

KG

Density: 0.91 g/cm³



Unlimited shelf-life



Nonflammable



UV-resistant

TECHNICAL SPECIFICATIONS

Resistant to chemical agents

Melting temperature 160 - 170 °C

0.48 mm

Breaking load longitudinal 516.9 MPa

ASTM D 1929 Flash-point **350** °C

Alkali-resistant material

Young modulus 5.37 GPa

Auto-ignition temperature >400 °C

CONSUMPTION

Variable according to the performance to be achieved in the industrial flooring to be built (on average 1 to 2 kg for each cubic metre of concrete).

STORAGE AND CONSERVATION

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Protect from humidity.



PHOTO GALLERY







ADDITIONAL CONTENT

×

Bending test Readymesh PF-540 (RILEM TC 162-TDF)

Dosage of fibres	6.0 Kg/m³
fCT,L	3.425 MPa
fR,1	2.913 MPa
fR,2	2.660 MPa
fR,3	2.669 MPa
fR,4	2.594 MPa

WARNINGS AND PRECAUTIONS

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

