

Repar Monosteel

Passivating monocomponent cement, anticorrosive, for reinforcing rods



Cement slurry in monocomponent powder, passivating, light blue in colour, to be added with water, modified with superpozzolanic agents, flexibilising resins and corrosion inhibitors, for the passivating treatment of oxidised reinforcing rods, in the restoration of degraded concrete.

CUSTOMS CODE: 3824 5090

COMPONENTS: Single-component

APPEARANCE: Powder

AVAILABLE COLORS: Light blue

PACKAGING AND DIMENSIONS: Pail 2.5 kg - Pail 5 kg - Bag 25 kg

OBTAINED CERTIFICATIONS AND REGULATIONS



FEATURES AND BENEFITS

The anti-corrosive effectiveness of Repar Monosteel results from the high alkalinity and from the superpozzolanic reactivity of components. The specific corrosion inhibitor contained in the compound (DCI - Corrosion Inhibitor Agrément Certificate BBA** n.96/3232), conforming to the standard UNI 9747, is based on a reaction which is capable of making unavailable the ferrous ions for the supply of the electrochemical processes of corrosion. The polymeric components of Repar Monosteel also determine further increases in the effectiveness against corrosion, especially vis-à-vis the aggressive attacks arising from chlorides and sulphates. (BBA = British Board of Agrément).

FIELDS OF APPLICATION

Passivating protection treatments of the reinforcement rods in interventions of restoration of works and articles in reinforced concrete, in marine, mountain and industrial environments.

ALLOWED SUPPORTS

Concrete - Rusty reinforcement rods

PREPARATION OF SUPPORTS

Carefully remove non-adhering rust, present on the metal surfaces of the exposed reinforcement rods by blasting or deep brushing , until the following condition is reached: "almost white metal" (metal colour as if it has just come out of extrusion).

MODE OF USE

Pour about half a litre of water into a bucket, add Repar Monosteel and additional water necessary for achieving a fluid, dense, brushable consistency. Continue mixing until a homogeneous lump-free mixture is obtained. Apply by brush on the surfaces of the previously prepared reinforcement rods.

APPLICATION METHODS

Brush

TOOL CLEANING

Water

KEY FEATURES

-  Highlighted product
-  Nonflammable
-  Temperature of use: +5 / +35 °C
-  Mix with water: 32-40 %
-  Shelf-life: 12 months
-  Use wearing protective gloves

TECHNICAL SPECIFICATIONS

UNI EN 1015/11
Compressive strength after 1 day **10 MPa**

UNI EN 1015/11
Flexural strength at 1 day **3 MPa**

EN 15183
Corrosion resistance **< 0.5 mm**

UNI EN 1542
Concrete adhesion (direct traction) * **2.4 N/mm²**

Fire resistance **A1**

UNI EN 1015-6
Density **1700 kg/m³**

Water/binder ratio **< 0.45**

UNI EN 1015/11
Compressive strength after 28 days **35 MPa**

UNI EN 1015/11
Flexural strength after 28 days **8 MPa**

EN 15184
Resistance to the extraction of the steel bars with improved adhesion **> 90 %**

pH **> 12**

Darcy impermeability **1 x 10 E-10 cm/s**

CONSUMPTION

From 0.02 to 0.07 kg of Repar Monosteel for each linear metre of steel bar to be treated.



STORAGE AND CONSERVATION

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.

PHOTO GALLERY



ADDITIONAL CONTENT



Produced and distributed by **AZICHEM srl**
Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
Tel: +39 0376.604185 / 604365
Fax: +39 0376 604398
www.azichem.com - info@azichem.com

Update of **15-07-2022**
Terms of sale and legal notices available at
<https://www.azichem.com/general-sales-conditions>
Total pages of this document: 4

WARNINGS AND PRECAUTIONS

The overflow of the product on the concrete adjacent to the treated rids does not entail any problem. The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

