

Sanacork

Sprayed cork finish for thermo-acoustic insulation



CUSTOMS CODE: 3214 9000
COMPONENTS: Single-component
APPEARANCE: Paste
AVAILABLE COLORS: White
PACKAGING AND DIMENSIONS: Pail 12 kg - Pallet: 36 x (Pail 12 kg)

ALLOWED SUPPORTS

Concrete - Cement-based or lime-based mortars - Prefabricated concrete - Drywall - Wood - Metal surfaces - Plastic - Fiber-cement - Tiles - Bricks - Polystyrene - Natural stones - Calcestruzzo armato - Lime and lime-cement plasters and mortars












APPLICATION METHODS

Low pressure airless nebulizer

TOOL CLEANING

Water

KEY FEATURES

- | | |
|--|--|
|  Density: 0.5 - 0.7 g/cm ³ |  Material 100% eco-friendly |
|  Maximum diameter of aggregate: 0.8 mm |  Min. recommended thickness: 3 mm |
|  Nonflammable |  Shelf-life: 12 months |
|  Solvent-free |  Temperature of use: +5 / + 45 °C |
|  To be applied in two coats |  Use wearing protective glasses |
|  UV-resistant | |

TECHNICAL SPECIFICATIONS

UNI-EN 13501 :2002

Reaction to fire **B s2 d0**

20°C

Touch hardening at 20°C **30 min**

Complete hardening at 20°C **12 - 24 h**

λ UNI EN 12667:2002

Thermal conductivity **0.058 W/mK**

CONSUMPTION

Approximately 1.8 - 2.0 kg/m² of Sanacork to make 3 mm thick in two coats with an airless gun.

STORAGE AND CONSERVATION

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Store the product at a temperature between +5°C and +35°C.

WARNINGS AND PRECAUTIONS

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

