

Sanafast

Setting and hardening accelerator



Sanafast is a specially formulated premix that, added during the mixing phase to our mortars (REPAR, GROUT, FLOOR, RINFOR lines) and to our natural hydraulic lime-based injection products (Sanafluens, Mikrosana), allows to accelerate the setting and hardening, with a much faster development of mechanical strength.

CUSTOMS CODE: 3824 5090 COMPONENTS: Single-component

APPEARANCE: Powder AVAILABLE COLORS: White

PACKAGING AND DIMENSIONS: Bag 25 kg - Pail 10 kg

FEATURES AND BENEFITS

Sanafast is formulated with a fast-setting binder and very fine mineral fillers, perfectly compatible with Portland cements, pozzolanic cements and natural hydraulic lime.

FIELDS OF APPLICATION

Adaptation (acceleration) of the setting times of mortars and plasters, to be used when environmental and meteorological conditions would make them too "slow" compared to the requirements of use: for example in the winter period when temperatures are low.

ALLOWED SUPPORTS

Cement-based or lime-based mortars

MODE OF USE

Careful dry premixing of Sanafast with the product for which an acceleration of setting and hardening times is always recommended.

APPLICATION METHODS

To be added to other components



TOOL CLEANING

Water

KEY FEATURES



Nonflammable



Temperature of use: +5 / +35 °C



Shelf-life: 12 months



Use wearing protective gloves

CONSUMPTION

Sanafast can be mixed in any proportion with any hydraulic binder.

STORAGE AND CONSERVATION

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.

PHOTO GALLERY







ADDITIONAL CONTENT





WARNINGS AND PRECAUTIONS

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

