

Syntech HAG Stabiland

Polyurethane resin for sealing and stabilizing excavations and tunnels



CUSTOMS CODE: 3907 2999

COMPONENTS: Two-components

APPEARANCE: Liquid + Liquid

AVAILABLE COLORS: Amber

PACKAGING AND DIMENSIONS: Can 21.3 kg [A] - Can 25 kg [B] - Kit: 1 Can 21.3 kg [A] + 1 Can 25 kg [B]

ALLOWED SUPPORTS

Concrete - Bricks - Rock walls - Porphyry and natural stones - Calcestruzzo armato

APPLICATION METHODS

Injection - Pump

TOOL CLEANING

Thinner for resins

KEY FEATURES



Density: (A+B) 1.150 g/cm³



Quick setting product



Temperature of use: +10 / +30 °C



Use wearing protective gloves

A:B Mixing ratio: 1:1 _



Shelf-life: 12 months



Use wearing protective glasses

TECHNICAL SPECIFICATIONS

after 1 day without water
Concrete adhesion (direct traction) > **1.5 MPa**

without water EN 12190
Compressive strength after 1 day **70 MPa**

without water EN 13892-2
Flexural strength at 1 day **90 MPa**

after 1 day without water EN ISO 527
Breaking load longitudinal > **37 MPa**

20 °C
Viscosity **190 mPas**

Shore D
Hardness **75**


CONSUMPTION

Product consumption depends on the size of the void volume to be filled and on the expansive reaction that is triggered after mixing the two components in relation to the amount of water present.

STORAGE AND CONSERVATION

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity. Store the product at a temperature between +10°C and +30°C.

PHOTO GALLERY



Produced and distributed by **AZICHEM srl**
Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
Tel: +39 0376.604185 / 604365
Fax: +39 0376 604398
www.azichem.com - info@azichem.com

Update of **14-06-2025**
Terms of sale and legal notices available at
<https://www.azichem.com/general-sales-conditions>
Total pages of this document: 3

WARNINGS AND PRECAUTIONS

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge. Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage. Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

